

RESIFA™ SOLESPHERE™ for 3D Printing Applications

RESIFA™ SOLESPHERE™ Silica for 3D Printing Resins / Additive Manufacturing

Multi-porous H-Series: High Specific Surface Area

		H-31	H-51	H-121	H-201
Mean particle size	μm	3	5	12	20
Specific surface area	m ² /g	800	800	800	800
Pore volume	mL/g	0.9	0.9	0.9	0.9
Pore diameter	nm	4.5	4.5	4.5	4.5
Oil absorption	mL/100g	150	150	150	150

Multi-porous H-Series: High Oil Absorption Capacity

		H-32	H-52	H-122	H-202	H-33	H-53
Mean particle size	μm	3	5	12	20	3	5
Specific surface area	m ² /g	700	700	700	700	700	700
Pore volume	mL/g	1.6	1.6	1.8	1.8	1.8	1.8
Pore diameter	nm	10	10	10	-	11	11
Oil absorption	mL/100g	300	300	300	300	400	400





RESIFA™ SOLESPHERE™ for 3D Printing Applications

Multi-porous L-Series: Low Specific Surface Area

		L-31	L-51	L-121	L-201
Mean particle size	μm	3	5	12	20
Specific surface area	m ² /g	300	300	300	300
Pore volume	mL/g	0.9	0.9	0.9	0.9
Pore diameter	nm	12	12	12	12
Oil absorption	mL/100g	150	150	150	150

Non-porous NP-Series

		NP-30	NP-100	NP-200
Mean particle size	μm	4	10	20
Specific surface area	m ² /g	40	50	100
Pore volume	mL/g	0.05	0.1	0.1
Pore diameter	nm	-	-	-
Oil absorption	mL/100g	30	35	40

RESIFATM and SOLESPHERETM are registered trademarks of AGC Inc.



AGC Chemicals Company AGC Inc.

Shin-Marunouchi Bldg. 1-5-1 Marunouchi Chiyoda-ku, Tokyo 100-8405 Japan Tel: +81-3-3218-5438 www.agc-chemicals.com

AGC Asia Pacific Pte., Ltd.

460 Alexandra Road #32-01 mTower Singapore 119963 Tel: +65 6273 5656 www.agc-asiapacific.com

AGC Chemicals Trading (Shanghai) Inc.

Room 4008/09, F40, T1 Raffles City Changning No.1133 Changning Road Shanghai, China 200051 Tel: +86-21-6386-2211 www.agcsh.com

AGC Chemicals Europe, Ltd.

Hillhouse International
Fleetwood Road North
Thornton-Cleveleys
FY5 4QD
United Kingdom
Tel: +44 (0) 1253 209560
www.agcce.com

AGC Chemicals Europe, Ltd. Commercial Centre

World Trade Center, Zuidplein 80 1077 XV Amsterdam, Netherlands Tel: +31-(0)-20-880-41-70 www.agcce.com

AGC Chemicals (Thailand) Co., Ltd.

944 Mitrtown Office Tower, 14th Floor Rama 4 Road, Wangmai Sub-District Pathumwan District, Bangkok 10330 Thailand Tel: +66-2-092-6499 www.acth.co.th

AGC Vidros do Brasil Ltda.

Estrada Municipal Doutor Jaime Eduardo Ribeiro Pereira, 500 Jardim Vista Alegre Guaratinguetá, SP, Brasil CEP 12523-671 Tel: +55 12 3127-7100 www.agcchem.com/pt-br/





AGC Chemicals Americas, Inc.

55 E. Uwchlan Avenue, Suite 201 Exton, PA 19341 United States of America

Telephone: +1 610-423-4300 Toll Free (US only): 800-424-7833 Fax: +1 610-423-4305

www.agcchem.com

Visit our website for compliance information and industry certifications.

The information provided herein is related only to the specific product designated and may not be applicable where such product is used in combination with any other materials or in any process.

NO REPRESENTATION OR WARRANTIES, EITHER EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE, ARE MADE HEREUNDER.

The user of this product has the sole responsibility to determine the suitability of the product for any use and manner of use intended. This document may be revised after its issuance, and the user is advised to use the latest revision.

This information should be used as a guide only and not to establish specification limits or design criteria.